

# Wash & Prime



## PRODUCT DESCRIPTION

The IPP Wash & Prime is a clear, low viscosity, water-based rinseable primer.

## RECOMMENDED USES

The Wash & Prime is designed to act as a cleaner primer for single ply membranes by breaking the chemical Bond of the inorganics on the surface of the membrane preparing it for a coating.

## PRODUCT CHARACTERISTICS

Color.....	Clear
Solubility in water.....	100% Soluble
VOC Content.....	0 g/l
pH.....	13 - 13.5
Specific Gravity.....	1.01
Set time to rinse.....	10 - 15 minutes

## PERFORMANCE TIPS

- A Squeegee is recommended to push excess water to the drains to accelerate drying.
- Surface must be rinsed well with no remaining residue.

## SAFETY PRECAUTION

Refer to the MSDS sheet before use. Published technical data and instructions are subject to change without notice. Contact IPP for additional technical data and instructions.

## SURFACE PREPARATION

Any necessary repairs or replacement of deck and/or insulation must be completed. The membrane must be dry and free of all visible dirt and debris prior to applying the Wash & Prime.

## APPLICATION CONDITIONS

Do not apply below 50° (10° C) or when rain is forecast. Read the MSDS thoroughly before handling. KEEP FROM FREEZING.

## DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and IPP makes no claim that these tests or any other tests, accurately represent all environments.

## APPLICATION PROCEDURES

Surface Preparation must be completed as indicated. *Mixing Instructions:* This product has excellent suspension and requires minimal stirring. **DO NOT THIN.** *Application Rate:* 400 - 500 square feet per gallon.

## APPLICATION EQUIPMENT

Inspect preliminary work relating to substrate for problem areas to ensure all preparatory work has been properly completed. Use a 2 - 3 gallon tank type pressure sprayer. Adjust the nozzle to achieve a uniform spray pattern with a 3 - 4 foot arc. Conventional airless spray equipment using a .015 - .017 tip may also be used. Allow the Wash & Prime to stand 10 - 15 minutes to wet out and react with the membrane. High pressure rinse the membrane using a minimum 2,000 PSI pressure washer, keeping the tip within 12" of the surface. A squeegee is recommended to push excess water to the drains to accelerate drying. After cleaning, if the appearance is dull and weathered, reapply the Wash & Prime. Surface must be dry prior to application of a coating.

## CLEAN-UP INSTRUCTIONS

Inspect completed application and correct any defects. Manufacturer's representatives may inspect the completed system and notify the contractor of any defects in the application. Clean up all debris, excess materials and equipment, and remove from site. Restrict traffic to only essential personnel. Provide appropriate protection against traffic and construction activities on the substrate

## WARRANTY

This product is manufactured of good materials and by competent workmen. Seller's and manufacturer's only obligation shall be to replace such quantity of product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising from use or the inability to use the product for his/her intended use, and user assumes all the risk.